



LEGAL DATA:
C.F e Reg.Imp.Novara: 02041920030
CCIAA Novara REA: 211799
P.IVA: IT02041920030
Codice Export: No015724
Cap.Soc.: 119.000 Iv

CONTACTS:
WEBSITE: www.u-power.it/it
EMAIL: info@u-power.it
TEL: +39 0322 53 94 01
FAX: +39 0322 23 00 01

REV. 27/05/2024

PRODUCT PICTURE

RANGES

TECHNOLOGIES

UB10109 HUNTER OB SR
Confort 11
SHOE TYPE "B"
SIZE RANGE 35-48
Size tested: 42 - WEIGHT 1.041



URBAN



DESCRIPTION	TECHNICAL SPECIFICATIONS	EN ISO STANDARD	VALUE
The shoe HUNTER is equipped with a soft leather upper with black microfiber inserts, lining and leather tongue that ensures comfort and well-being of the foot.	SAFETY TOE CAP	20347:2022	RESULT
	Impact resistance. Free heights after collision mm	≥ 14	N.A.
	Compressive strength. Free heights after compr. mm	≥ 14	N.A.
The perforated toe ensures greater breathability. Comfort is also increased by the leather insole and the polyurethane sole with Infinergy® insert.	INSOLE “N.A.”		
	Puncture resistance N	≥ 1100	N.A.
	ELECTRICAL RESISTANCE CATEGORY	< 10 ⁹ Ω	N.A.
Infinergy® insert, the soul of this revolutionary shoe is the technology that stores over 55% of energy and returns it at every step.	UPPER DYNAMIC WATERPROOFING AFTER 60'		
	Water absorption after 60'	≤ 30%	N.A.
	Water transmitted after 60'	≤ 0.2 gr	N.A.
Born for the world of running, Infinergy® has transformed the traditional cushioning into dynamic cushioning, which uses the movement of the foot to store energy in the ground grip phase and return it when the foot pushes forward.	Permeability to water vapor mg/(cm ² h)	≥ 0.8	1.0
	Permeability coefficient mg/cm ²	≥ 15	20.1
	VAMP LINING		
	Permeability to water vapor mg/(cm ² h)	≥ 2	16.9
	Permeability coefficient mg/cm ²	≥ 20	142.3
	Resistance to abrasion - DRY cycles	25600 cycles	No hole
	Resistance to abrasion - WET cycles	12800 cycles	No hole
	INSOLE		
	Abrasion resistance	≥ 400 cycles	No damage
	SOLE WEAR		
The first LIFESTYLE shoe branded U-Power characterized by: - attractive look - sporty design - amazing comfort	Abrasion resistance (volume loss) mm ³	≤ 150	28
	Bending resistance mm	≤ 4	0.8
	Resistance to sole / midsole detachment N/mm	≥ 3	3.6
	Heel energy absorption J	≥ 20	N.A.
	SLIP RESISTANCE		
	Slip resistance on ceramic with NaLS (heel forward 7°)	≥ 0.31	0.45
	Slip resistance on ceramic with NaLS (heel back 7°)	≥ 0.36	0.42
	SR-Slip resistance on ceramic with glycerin (heel forward 7°)	≥ 0.19	0.32
	SR-Slip resistance on ceramic with glycerin (heel back 7°)	≥ 0.22	0.25