

## U GROUP SRL

Via Borgomanero nº 1 28040 Paruzzaro (NO)

## **LEGAL DATA:**

Cap.Soc.:

C.F e Reg.Imp.Novara: CCIAA Novara REA: P.IVA: Codice Export: 02041920030 211799 IT02041920030 No015724 119.000 lv

## CONTACTS: WEBSITE: EMAIL: TEL: FAX:

www.u-power.it/it info@u-power.it +39 0322 53 94 01 +39 0322 23 00 01

REV. 27/05/2024

**DATA SHEET** 

PRODUCT PICTURE

**RANGES** 

**TECHNOLOGIES** 

UB20029 HELIX OB SR Confort 11 SHOE TYPE "A" SIZE RANGE 35-48 Size tested: 42 - WEIGHT 1.004















DESCO	PTION
DESURI	FILON

The shoe HELIX is equipped with a soft leather upper, suede inserts, inner lining in soft cotton sponge that ensures comfort and well-being of the foot. Perforated toe to ensure greater breathability. Comfort is also increased by the leather insole and the polyurethane sole with Infinergy® insert.

Infinergy® insert, the soul of this revolutionary shoe is the technology that stores over 55% of energy and returns it at every step.

Born for the world of running, Infinergy® has transformed the traditional cushioning into dynamic cushioning, which uses the movement of the foot to store energy in the ground grip phase and return it when the foot pushes forward.

The first LIFESTYLE shoe branded U-Power characterized by:

- attractive look
- sporty design
- amazing comfort

TECHNICAL SPECIFICATIONS	EN ISO STANDARD	VALUE
SAFETY TOE CAP	20347:2022	RESULT
Impact resistance. Free heights after collision mm	≥ 14	N.A.
Compressive strength. Free heights after compr. mm	≥ 14	N.A.
INSOLE "N.A."		
Puncture resistance N	≥ 1100	N.A.
ELECTRICAL RESISTANCE CATEGORY	$< 10^{9}\Omega$	N.A.
UPPER DYNAMIC WATERPROOFING AFTER 60'		
Water absorption after 60'	≤ 30%	N.A.
Water transmitted after 60'	≤ 0.2 gr	N.A.
Permeability to water vapor mg/(cm <sup>2</sup> h)	≥ 0.8	1.0
Permeability coefficient mg/cm <sup>2</sup>	≥ 15	20.1
VAMP LINING		
Permeability to water vapor mg/(cm <sup>2</sup> h)	≥ 2	24.6
Permeability coefficient mg/cm <sup>2</sup>	≥ 20	199.2
Resistance to abrasion - DRY cycles	25600 cycles	No hole
Resistance to abrasion - WET cycles	12800 cycles	No hole
INSOLE		
Abrasion resistance	≥ 400 cycles	No damage
SOLE WEAR		
Abrasion resistance (volume loss) mm <sup>3</sup>	≤ 150	28
Bending resistance mm	≤ 4	0.8
Resistance to sole / midsole detachment N/mm	≥3	3.6
Heel energy absorption J	≥ 20	N.A.
SLIP RESISTANCE		
Slip resistance on ceramic with NaLS (heel forward 7°)	≥ 0.31	0.45
Slip resistance on ceramic with NaLS (heel back 7°)		0.42
SR-Slip resistance on ceramic with glycerin (heel forward 7°)	≥ 0.19	0.32
SR-Slip resistance on ceramic with glycerin (heel back 7°)	≥ 0.22	0.25